

CHANGXING JINGWEI BAMBOO PRODUCTS CO.,LTD
 HUIKAN TOWNSHIP,CHANGXING COUNTY,HUZHOU CITY,ZHEJIANG PROVINCE,CHINA

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description : ENGINEERED RIGID CORE TIMBER FLOOR
 SGS Ref. No. : SDFS1908005034FF
 Sample Receiving Date : Aug.13, 2019
 Test Performing Date : Aug.13, 2019 to Aug.20, 2019

Test Result Summary

Test(s) Requested	Result(s)	Comments
AS ISO 9239-1:2003 Reaction to fire tests for floorings - Part 1: Determination of the burning behaviour using a radiant heat source	Refer to next page(s).	/
For further details, please refer to the following page(s)		

Signed for and on behalf of
 Shunde Branch
 SGS-CSTC Co., Ltd.




Heather Meng
 Approved signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Inspection & Testing Services Co., Ltd.
 Shunde Branch Harbin

1/F, 1st Building, European Industrial Park, No.1 Shunde South Road, Wusha Section, Daliang Town, Shunde, Foshan, Guangdong, China 528333 t (86-757)22805888 f (86-757)22805858 www.sgs.com.cn
 中国·广东·佛山市顺德区大良街道办事处五沙顺和南路1号欧洲工业园一号厂房首层 邮编: 528333 t (86-757)22805888 f (86-757)22805858 e sgs.china@sgs.com

Test Conducted:

AS ISO 9239-1:2003 Reaction to fire tests for floorings - Part 1: Determination of the burning behaviour using a radiant heat source

General Information:

Area density:	About 12.8kg/m ²
Thickness:	About 6.8mm
Conditioning of test specimen:	Prior to testing, all specimens were conditioned at temperatures of (23±2)°C and at a relative humidity of (50±5)% to constant mass.
Mounting and fixing (for AS ISO 9239-1:2003):	Specimen width less than 230 mm, joining together two pieces of samples to 230 mm wide. Spelling a seam in the middle of the 230 mm width position. Fibre cement board, with its density about 1800kg/m ³ , thickness about 8mm, is as the substrate. The specimens were fixed mechanically to the substrate.

Test Result:

Specimen No.	Furthest extent of spread of flame(mm)	Critical Heat Flux (CHF or HF-30) kW/m ²	Comments and Observation
1	420	4.84	Charring
2	430	4.68	Charring
3	410	5	Charring

The mean value for the critical heat flux (CHF and/or HF-30) from the three specimens from the same orientation: 4.84kW/m²

Smoking measurement
Integrated smoke value: 97.9%•min

Statements:


The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.




Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Photo Appendix:



Sample face



Sample back

End of Report

