

CHANGXING JINGWEI BAMBOO PRODUCTS CO.,LTD  
 HUAIKAN TOWNSHIP,CHANGXING COUNTY,HUZHOU CITY,ZHEJIANG PROVINCE,CHINA

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description : ENGINEERED RIGID CORE TIMBER FLOOR  
 Sample Receiving Date : Aug.08, 2019  
 Test Performing Date : Aug.12, 2019 to Aug.23, 2019

**Test Result Summary**

No.	Test item	Test(s) Requested(Method)	Result(s)	Comments
1	Heat stability	Client provide/WI-QA-054 (4)	Pass	/

For further details, please refer to the following page(s)

Signed for and on behalf of  
 Shunde Branch  
 SGS-CSTC Co., Ltd.




Peter Zhao  
 Approved signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443, or email: CN.Doccheck@sgs.com**

1/F, 1<sup>st</sup> Building European Industrial Park, No.1 Shunhe South Road, Wusha Section, Dailing Town, Shunde, Foshan, Guangdong, China 528333 t (86-757)22805888 f (86-757)22805858 www.sgs.com.cn  
 中国·广东·佛山市顺德区大良街道办事处五沙顺和南路1号欧洲工业园一号厂房首层 邮编: 528333 t (86-757)22805888 f (86-757)22805858 e sgs.china@sgs.com

**Test Information:**

Sample description: See photo

1. Test item: Heat stability

Test method: Client provide/WI-QA-054 (4)

Test condition:

Place the test specimens horizontally on to support plates, previously placed in the oven, and allow to come to (50±2) °C. Maintain the test specimens at this temperature for 48 h in the oven.

Test environment: (24±2) °C, (50±4) %RH

Test result:

Sample	Heat stability		Requirement of client	Conclusion
A	Cupping/Width	0.18%	≤0.2%	Pass
	Bowing/Length	0.30%	/	/
	Cracking/ft <sup>2</sup>	No visible crack	≤20cm	Pass

**Photo Appendix:**



Original sample

\*\*\*End of Report\*\*\*

